



## Megengedett üzemi nyomás

Hőmérséklet	Élettartam (év)	ABN//INSTAL CT FASER RD 3,2-SDR 7,4 széria		ABN//INSTAL CT FASER RD 5-SDR 11 széria		ABN//INSTAL CT FASER RD8-SDR 17 széria	
		bar	psi	bar	psi	bar	psi
10 °C	1	39.20	568.52	25.08	363.75	15.68	227.42
	5	38.20	554.04	24.40	353.89	15.28	221.61
	10	37.57	544.90	24.04	348.67	15.03	217.99
	25	36.75	533.01	23.52	341.12	14.70	213.20
	50	36.50	529.38	23.36	338.80	14.60	211.75
20 °C	100	35.95	521.41	23.00	333.58	14.38	208.56
	1	34.15	495.30	21.85	316.90	13.66	198.12
	5	33.05	479.34	21.15	306.75	13.22	191.74
	10	32.77	474.70	20.97	304.14	13.11	190.14
	25	32.00	464.12	20.48	297.03	12.80	185.64
30 °C	50	31.70	459.76	20.30	294.42	12.68	183.90
	100	31.15	451.79	19.93	289.06	12.46	180.71
	1	29.80	432.21	19.08	276.73	11.93	173.03
	5	29.00	420.60	18.56	269.19	11.60	168.24
	10	28.45	412.63	18.20	263.96	11.38	165.05
40 °C	25	27.90	404.65	17.85	258.89	11.16	161.86
	50	27.62	400.59	17.68	256.42	11.05	160.26
	100	27.05	392.32	17.31	251.06	10.82	156.93
	1	26.05	377.82	16.67	241.77	10.42	151.12
	5	25.20	365.49	16.12	233.80	10.08	146.19
50 °C	10	24.65	357.51	15.77	228.72	9.86	143.00
	25	24.37	353.45	15.60	226.25	9.75	141.41
	50	23.82	345.47	15.24	221.03	9.53	138.22
	100	23.52	341.12	15.05	218.28	9.41	136.48
	1	23.05	334.31	14.75	213.93	9.22	133.72
60 °C	5	22.17	321.54	14.19	205.80	8.87	128.64
	10	21.60	313.28	13.82	200.44	8.64	125.31
	25	21.30	308.93	13.63	197.78	8.52	123.57
	50	20.75	300.95	13.20	191.44	8.30	120.38
	100	20.45	296.60	13.00	188.54	8.18	118.64
70 °C	1	19.37	280.93	12.40	179.84	7.75	112.40
	5	18.80	372.67	12.03	174.48	7.52	109.06
	10	18.50	268.31	11.84	171.72	7.40	107.32
	25	17.92	259.90	11.47	166.35	7.17	103.99
	50	17.70	256.71	11.30	163.89	7.06	102.39
80 °C	1	16.55	240.03	10.59	153.59	6.62	96.01
	5	15.67	227.27	10.00	145.03	6.27	90.93
	10	15.40	223.35	9.85	142.86	6.16	89.34
	25	15.10	219.00	9.66	140.10	6.04	87.60
	50	14.90	216.10	9.50	137.78	5.93	86.00
95 °C	1	13.82	200.44	8.84	128.21	5.53	80.20
	5	13.22	191.73	8.46	122.70	5.29	76.72
	10	12.92	187.38	8.27	119.94	5.17	74.98
	25	12.70	184.19	8.10	117.48	5.06	73.38
95 °C	1	10.75	155.91	6.88	99.78	4.30	62.36
	5	10.15	147.21	6.49	94.12	4.06	58.88

Biztonsági tényező (SF) = 1,25

1bar = 14.5 psi



### CENTRAL

CTRA. BAÑOS DE ARTEIXO, 28  
PARQUE EMPRESARIAL AGRELA  
15008 A CORUÑA (SPAIN)

T. +34 902 202 532  
F. +34 902 253 240

### PRODUCTION PLANT (CERTIFIED)

PARQUE EMPRESARIAL MEDINA ON  
AUTOVÍA A-6, KM 152  
47400 MEDINA DEL CAMPO  
VALLADOLID (SPAIN)

INFO@GRUPOABN.COM

